

BEST AVAILABLE COPY

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁵ : C09K 3/14, B24B 1/00, B24C 1/00</p>	<p>A1</p>	<p>(11) International Publication Number: WO 95/02650</p> <p>(43) International Publication Date: 26 January 1995 (26.01.95)</p>		
<table style="width: 100%; border: none;"> <tr> <td style="width: 50%; border: none; vertical-align: top;"> <p>(21) International Application Number: PCT/US94/07586</p> <p>(22) International Filing Date: 13 July 1994 (13.07.94)</p> <p>(30) Priority Data: 08/093,123 16 July 1993 (16.07.93) US</p> <p>(71) Applicant: HENKEL CORPORATION [US/US]; Suite 150, 140 Germantown Pike, Plymouth Meeting, PA 19462 (US).</p> <p>(72) Inventor: HELD, Theodore, D., III; 5 Radnor Circle, Grosse Pointe Farms, MI 48236 (US).</p> <p>(74) Agent: WOOD, John, Daniel; Henkel Corporation, Suite 150, 140 Germantown Pike, Plymouth Meeting, PA 19462 (US).</p> </td> <td style="width: 50%; border: none; vertical-align: top;"> <p>(81) Designated States: AU, BR, CA, CN, JP, KR, RU, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report.</i></p> </td> </tr> </table>			<p>(21) International Application Number: PCT/US94/07586</p> <p>(22) International Filing Date: 13 July 1994 (13.07.94)</p> <p>(30) Priority Data: 08/093,123 16 July 1993 (16.07.93) US</p> <p>(71) Applicant: HENKEL CORPORATION [US/US]; Suite 150, 140 Germantown Pike, Plymouth Meeting, PA 19462 (US).</p> <p>(72) Inventor: HELD, Theodore, D., III; 5 Radnor Circle, Grosse Pointe Farms, MI 48236 (US).</p> <p>(74) Agent: WOOD, John, Daniel; Henkel Corporation, Suite 150, 140 Germantown Pike, Plymouth Meeting, PA 19462 (US).</p>	<p>(81) Designated States: AU, BR, CA, CN, JP, KR, RU, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report.</i></p>
<p>(21) International Application Number: PCT/US94/07586</p> <p>(22) International Filing Date: 13 July 1994 (13.07.94)</p> <p>(30) Priority Data: 08/093,123 16 July 1993 (16.07.93) US</p> <p>(71) Applicant: HENKEL CORPORATION [US/US]; Suite 150, 140 Germantown Pike, Plymouth Meeting, PA 19462 (US).</p> <p>(72) Inventor: HELD, Theodore, D., III; 5 Radnor Circle, Grosse Pointe Farms, MI 48236 (US).</p> <p>(74) Agent: WOOD, John, Daniel; Henkel Corporation, Suite 150, 140 Germantown Pike, Plymouth Meeting, PA 19462 (US).</p>	<p>(81) Designated States: AU, BR, CA, CN, JP, KR, RU, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report.</i></p>			
<p>(54) Title: AQUEOUS WET SANDING COMPOSITION AND USE THEREOF</p> <p>(57) Abstract</p> <p>An aqueous liquid composition containing glycerin and polyethylene glycol with a molecular weight in the range of about 400 to about 1,000, and, optionally, additional surfactant, is an excellent liquid auxiliary for wet sanding and produces a sanding mud that can easily be removed by washing with water, even after drying.</p>				

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

AQUEOUS WET SANDING COMPOSITION AND USE THEREOF

FIELD OF THE INVENTION

This invention relates to an aqueous liquid composition that is substantially free from volatile organic compounds ("VOC") and is useful directly as, or can be diluted with water to make a liquid useful directly as, the liquid auxiliary for wet sanding of organic surfaces such as the surfaces of various structural plastics and plastic sheet materials, including but not limited to polyolefins, polycarbonate esters, polyacetals, polyamides, filled thermosetting polyesters, and the like and also such organic surfaces as dried and/or cured paint, lacquer, primer, and like protective coating materials that comprise an organic binder and usually also pigment and/or dye and optionally fillers.

BACKGROUND OF THE INVENTION AND RELATED ART

In order to achieve the desired degree of surface finishing quality, it is often necessary to smooth or polish the surface of plastics and of dried and/or cured coatings of paints and like materials, particularly intermediate coats that are to be covered by another coating of paint or lacquer. This smoothing and/or polishing is most commonly accomplished by abrasive finishing or sanding, using an abrasive such as silicon carbide, garnet, iron oxide, or aluminum oxide, either in the form of a coated abrasive in which the abrasive grits are attached to some flexible backing or in a slurry of the abrasive grits with some liquid. If a coated abrasive is used, it is customary to utilize a liquid auxiliary during the sanding operation, in order to achieve optimum surface quality and avoid the generation of excessive dust, which would at best be annoying, and at worst could be seriously hazardous, to workers performing the sanding; dust could also damage wet protective coating materials on processed parts in the vicinity of the sanding operation by settling on the wet coatings and thereby making the surface rough when it is desired to be smooth. Therefore, whether a coated abrasive or a slurry is used initially, by the completion of the sanding operation the smoothed surface is normally covered with a mixture of a liquid carrier and suspended finely divided abrasive and solid organic particles. This mixture is commonly called "sanding mud" or simply "mud" in the abrasive art.

Before subsequent finishing operations, the sanding mud normally should be removed from the surface. Water or a water based rinse liquid is usually used to accomplish this removal, and sometimes power washing of the rinse liquid is used to assist in removing the sanding mud. In many instances, not even power washing will satisfactorily remove the sanding mud, so that hand rubbing or wiping, with substantial expense that would preferably be avoided, is required in order to achieve adequate surface quality.

In many instances in the prior art, a mixture of isopropyl alcohol (hereinafter often abbreviated "IPA") or a conventional dishwashing detergent liquid and water has been used as the sanding liquid auxiliary; water without any special additive is also frequently used. These types of liquid auxiliary have proved to be at least moderately satisfactory when the sanding mud formed in the course of using it is promptly washed away after completion of sanding. However, in certain assembly line manufacturing operations, it has been found that the time between sanding and washing is long enough for the sanding mud formed during use of these types of liquid auxiliary to dry sufficiently to resist ready removal by rinsing, or even by power washing, with water. Even in manufacturing operations where such drying does not occur during operation under most conditions, it can still occur during interruptions of normal processing conditions, such as occur during rest periods for the operators, which may include as much as two-thirds of the time in a day in single worker shift operations, or as a result of mechanical malfunctions of the operations. Also, IPA is of course a regulated VOC. Accordingly, a major object of this invention is to provide a superior aqueous liquid auxiliary for sanding that is substantially free from VOC's and is readily removed by water rinsing, even after substantial times of exposure to normal ambient air. Another object is to provide a technically satisfactory aqueous liquid auxiliary containing only ingredients that are harmless to human skin, in view of the virtual practical impossibility of preventing contact between the liquid auxiliary used in wet sanding by hand and the skin of the workers performing the sanding. Other objects will be apparent from the description below.

DESCRIPTION OF THE INVENTION

Other than in the operating examples and claims, or where otherwise expressly

indicated, all numbers expressing conditions of use or quantities of ingredients used herein are to be understood as modified in all instances by the term "about" in describing the broadest aspects of the invention. Practice within the numerical limits given is generally preferred, however. Also, unless expressly stated to the contrary: percent values are by weight; the description of a group or class of materials as suitable or preferred for a given purpose in connection with the invention implies that mixtures of any two or more of the members of the group or class are equally suitable or preferred; description of constituents in chemical terms refers to the constituents at the time of addition to any combination specified in the description, and does not necessarily preclude chemical interactions among the constituents of a mixture once mixed; specification of materials in ionic form implies the presence of sufficient counterions to produce electrical neutrality for the composition as a whole; and any counterions thus implicitly specified should preferably be selected from among other constituents explicitly specified in ionic form, to the extent possible; otherwise such counterions may be freely selected, except for avoiding counterions that act adversely to the stated objects of the invention.

Summary of the Invention

One major embodiment of the present invention is a sanding liquid auxiliary composition that comprises, preferably consists essentially of, or most preferably consists of, water and:

- (A) from 1.0 to 50 %, preferably from 5.0 to 25 %, more preferably from 10.0 to 20 %, or still more preferably from 13.0 to 18.0 %, of dissolved polyol molecules selected from the group consisting of molecules that include from 2 - 6 carbon atoms and at least two-thirds as many hydroxyl groups as carbon atoms, preferably with no other atoms than carbon, hydrogen, and oxygen, independently preferably with at exactly as many hydroxyl groups as carbon atoms, most preferably glycerin; and
- (B) from 0.5 to 40 %, preferably from 0.8 to 16 %, more preferably from 1.0 to 10 %, or still more preferably from 2.0 to 6.0 %, of dissolved hydroxy terminated polyoxyethylene (also called "polyethyleneglycol") having a weight average molecular weight in the range from 200 to 4000, preferably in the range

from 300 to 1900, or more preferably in the range from 400 to 1000; and, optionally,

- (C) from 0.01 to 5 %, preferably from 0.1 to 4 %, or more preferably from 0.5 to 2.5 % total of surfactant not within the scope of components (A) and (B), preferably alkylpolyglucoside surfactant.

An alkyl polyglucoside is a compound of the formula I:



where R^1 is a monovalent organic moiety containing from one to 30 carbon atoms; G represents a divalent moiety (except for one monovalent terminal moiety) derived from a reducing saccharide containing 5 or 6 atoms by removing hydrogen atom(s) therefrom; and n is a number having an average value from 1 to 6.

Compositions as described immediately above are "working" compositions, i.e., they are suitable for direct use as an auxiliary by application to an organic surface before the surface is sanded. A composition of the invention can also be provided as a concentrate intended for dilution with water before use. Other embodiments of the invention include a process of using a composition according to the invention for a sanding liquid auxiliary and a sanding process using a composition according to the invention as liquid auxiliary.

Description of Preferred Embodiments

Preferably all the ingredients of the compositions according to the invention are selected from materials with well-established harmlessness to human skin. Hypoallergenic materials such as glycerin and alkyl polyglucosides are especially preferred for this reason among others.

Preferably the ratio by weight between component (A) and component (B) in a composition according to this invention is within the range from 30:1 to 1:1, more preferably within the range from 10:1.0 to 2.0:1.0

Preferably a composition according to the invention does not substantially swell or dissolve the organic solid to be sanded. This property can conveniently be checked by placing a few drops of the composition on a sample of the surface to be sanded, allowing the drops to remain in place on the surface for at least eight hours, and then rinsing off the composition and examining the surface for visible damage. Most

preferably, no change in the surface to be sanded is observable with the unaided eye after this test. In some cases, however, a faint haziness is observable in the tested surface after such an extended test, without any significant harm to the performance of the composition that causes the haze in practical use. Compositions that leave the surface to be sanded visibly swollen, blistered, and/or tacky are preferably avoided.

Individual components can be tested in the same way as described above for the compositions, if the individual components are liquid, or in concentrated solutions if the components are solids at the intended sanding temperature. Most surfactants tested have been found to promote swelling of the surfaces to be sanded, but alkyl polyglucosides are exceptional in lacking any such detrimental tendency. If a surfactant is needed or preferred in the composition, therefore, this class of surfactants is preferred.

The most common reason for using a surfactant is to promote spreading of the liquid auxiliary over the surface to be sanded. The amount of surfactant used, if any, preferably is sufficient to cause a contact angle between the liquid auxiliary and the surface to be sanded that is, with increasing preference in the order given, no more than 95, 35, 20, 12, or 6, degrees.

The amount of liquid auxiliary material needed for effective sanding can not be exactly specified, but it can readily be determined by those of ordinary skill in the art, taking account of the amount of sanding to be done and the nature of the substrate being sanded, with some slight experimentation possibly being required. It is believed that the minimum amount of active substances (i.e., components (A), (B), and (C) if used) in the liquid auxiliary needed for effective operation according to the invention may be correlated with the surface area of sanding swarf produced, analogously to the well known phenomenon of the "oil demand" of paint pigment particles. As a general guideline, however, for a working liquid auxiliary composition containing 20 % of active ingredients, an amount of liquid auxiliary corresponding to at least 25 milliliters ("ml") per square meter (" m^2 ") of surface to be sanded is preferred, an amount of at least 125 ml/ m^2 is more preferred, and an amount of at least 350 ml/ m^2 is still more preferred, when the surface is sanded with abrasive grits having a standard grading size of 400 to 600 (corresponding to median particle sizes from 30 to 15 microns). For

more or less concentrated liquid auxiliaries, the amount of liquid auxiliary can be adjusted accordingly to provide the same amount of active ingredient per unit area of surface sanded.

Polyethylene glycols sold by Dow Chemical Company under the trade name of POLYGLYCOL E and by BASF under the trade name PLURACOL are among those useful in the practice of the invention and readily available. Polyethylene glycols have the formula $H(OCH_2CH_2)_nOH$, and those where n on average is in the range of about 4 to about 11 are most useful for component (B) of a composition according to the invention. In the commercially available polyethyleneglycols the trade name is usually followed by a number which corresponds to the average molecular weight of the product, and this convention is followed herein, using the generally art recognized abbreviation "PEG" for polyethyleneglycols, instead of the specific trade name. For example, for PEG 400, $n = 8.2 - 9.1$, and the molecular weight, which is to be understood herein as weight average molecular weight, would be about 400.

Component (C) when used is preferably selected from nonionic and/or amphoteric (also called "ampholytic") surfactants only. Commercial surfactants such as TRITON® DF-54 (modified polyethoxy adduct), TRITON® DF12 (modified polyethoxylated linear alcohol); Triton® DF-16 (a terminated ethoxylated linear alcohol), products of Union Carbide Corporation; MAKON® NF-12 (an alkylphenoxypolyoxyethylene alcohol) manufactured by Stepan Company; and PLURONIC® L62 (a polyoxyethylene polyoxypropylene block copolymer) manufactured by BASF Wynadotte Corporation are examples of nonionic surfactants that can be used for component (C). Typical useful amphoteric surfactants include the following commercially available products: MONATERIC® CyNa50, a 50 % active solution of the sodium salt of 2-caprylic-1-(ethyl beta oxypropionic acid)-imidazoline by Mona Industries, and ALKAWET® LF, a proprietary amphoteric surfactant blend manufactured by Lonza. However, as already noted, the most preferred surfactants are the (nonionic) alkyl polyglucosides, which are commercially available from Henkel Corporation under the trade name APG®.

As already noted briefly above, the process according to this invention is most useful when some time elapses between the completion of sanding and the removal of

the sanding mud from the sanded surface. With increasing preference in the order given, therefore, it is preferred that a process according to this invention include a time delay of at least 0.5, 1.0, 2.5, 4.6, 7.1, 12.0, 20, or 30 minutes between the completion of sanding and the beginning of rinsing to remove sanding mud from the sanded surface.

The practice of the invention can be further appreciated from the following nonlimiting examples and comparison examples.

Examples Group I

Three working compositions according to the invention were prepared with the ingredients shown in Table 1.

Table 1			
Ingredient	Percent of Ingredient in Example No.:		
	1	2	3
Glycerine	18.0	14.0	13.0
PEG 400	2.0	-	1.0
PEG 1000	-	4.0	5.0
MONATERIC® CyNa50	-	2.0	-
APG® 325	-	-	1.0

The composition of Example 1 remains as a bead when placed on a typical dried primer coat surface, having an estimated contact angle of at least 90 °. The composition of Example 2 spreads spontaneously over the same surface, having a contact angle not much more than 0 °. The composition of Example 3 is intermediate in wetting power between the other two.

All three compositions were tested on panels precoated with U04AD045 gray primer from BASF Corporation and on other panels precoated with "80° Gloss" RIM primer from PPG Corp. When ten drops of each formulation (having a total volume of 0.5 ml) were applied to a surface area of 5 square centimeters on each panel, excellent sanding lubrication was achieved when sanding with 3M Type 286 L Grit 400 Waterproof coated abrasive paper. The sanding mud was allowed to stand for 8 hours

in air at 43° C and 60 % relative humidity ("RH"). The sanding mud from Example 1 was very quickly washed away from the PPG primer with ordinary rinsing only, but a slight amount of sanding mud was left on the other panels tested after such ordinary rinsing, with the least amount left on panels with the formulation of Example 1 and the most with the formulation of Example 2. The sanding mud from all these tests was readily removed by conventional power washing, using a 2 % concentration of PARCO® Plastic Cleaner 2501 in water at 57° C for a contact time of 60 seconds ("sec"), followed by 30 sec rinse with ambient temperature tap water and a second 30 sec rinse with ambient temperature deionized water, and finally blowing dry with compressed air.

All the formulations were separately tested for attack on the substrates, without doing any abrasive finishing, under exposure for 8 hours at 49° C and 25 % RH. The only evidence of attack on the substrate was a very slight slick remnant on the BASF primer with the formulation of Example 1.

Example and Comparison Example Components Group II

In this group, various candidate components were tested for possible damage to substrates. A few drops of each component were placed on the surface of test substrates as described further below and allowed to stand for 8 hours in air at 49° C and 25 % RH; then the residue of the liquid auxiliary was rinsed away with 60 seconds of water spraying. The substrates tested and their identifying numbers are:

1. U04AD045 gray primer from BASF Corporation
2. Premix gray SMC primer from Siebert-Oxidermo Corporation
3. XENOY™ polycarbonate/polyester blend plastic from General Electric
4. Red Spot Paint Company type 206LE 2K Polyurethane Topcoat, white
5. "80° Gloss" RIM primer from PPG Corporation.

The components tested and their identifying abbreviations (in parentheses) are: APG® 225 (Apg2) and APG® 325 (Apg3) from Henkel Corp.; PEG 400 (P400), PEG 1000 (P 1000), and PEG 6000 (P 6000); glycerine (GLYC); Triton® DF-16 (DF-16); MAKON® NF-12 (NF-12); MONATERIC® CyNa50 (MON) and PLURONIC® L63 (PLU). The results are shown in Table 2. Only glycerine, APG® surfactants, and PEG 1000 were generally free from any evidence of damage when applied in full

strength as in this test, but many of the other components listed can be used in the amounts preferred for working compositions according to the invention, without causing any unacceptable damage to the surfaces sanded.

Table 2					
Component	Evidence of Damage on Substrate No.:				
	1	2	3	4	5
Apg2	trace	none	none	none	none
Apg3	none	none	none	none	none
P 400	flat, whitish raised area	shiny raised area	haze damage	whitish raised bump	raised area
P 1000	nm	nm	nm	nm	none
P 6000	nm	nm	nm	nm	none, but dried mud difficult to remove
GLY	nm	nm	nm	nm	none
DF 16	slick	shiny raised area	haze damage	whitish raised bump	bump
MON	trace	trace	haze damage	slight raised area	raised area
NF 12	glossy raised slick	glossy, slightly raised	haze damage	raised area	raised area
PLU	glossy raised slick	glossy, slightly raised	raised area	raised area	raised area
Note for Table 2: "nm" means not measured.					

Comparison Examples Group III

The commercially available dishwashing detergents DAWN®, DOVE®, IVORY CLEAR®, and JOY® were tried at 2 % active ingredient concentration in water as wet sanding auxiliary liquids under the same general conditions as described in Groups I and

- 5 II. All of them proved substantially ineffective in producing sanding muds that could easily be removed after 8 hours drying. If used as supplied, with about 20 % active ingredients, or at any concentration down to about 2.5 %, these commercial liquid detergents are too viscous to perform satisfactorily as sanding auxiliaries for wet sanding with fine coated abrasive such as Grit 400.

10

What is claimed is:

CLAIMS

1. A sanding liquid auxiliary composition that consists essentially of water and:
 - (A) from about 1.0 to about 50 % of dissolved polyol molecules selected from the group consisting of molecules that include from 2 - 6 carbon atoms and at least two-thirds as many hydroxyl groups as carbon atoms; and
 - (B) from about 0.5 to about 40 % of dissolved hydroxy terminated polyoxyethylene having a weight average molecular weight in the range from about 200 to about 4000; and, optionally,
 - (C) from about 0.01 to about 5 % total of surfactant not within the scope of components (A) and (B).
2. A composition according to claim 1, wherein the concentration of component (A) is within the range from about 5.0 to about 25 %, the concentration of component (B) is within the range from about 0.8 to about 16 %, and the amount of component (C) is at least about 0.01 %.
3. A composition according to claim 2, wherein the amount of component (C) is from about 0.1 to about 4 % and component (C) is selected from nonionic and ampholytic surfactants.
4. A composition according to claim 3, wherein the concentration of component (A) is within the range from about 10.0 to about 20 % and the concentration of component (B) is within the range from about 1.0 to about 10 %.
5. A composition according to claim 4, wherein component (A) is selected from molecules including no other atoms than carbon, hydrogen, and oxygen; and component (B) is selected from polyoxyethylene with a weight average molecular weight in the range from about 300 to about 1900.
6. A composition according to claim 5, wherein component (A) is selected from molecules including as many hydroxyl groups as carbon atoms; and component (B) is selected from polyoxyethylene with a weight average molecular weight in the range from about 400 to about 1000.
7. A composition according to claim 6, wherein component (A) is glycerin.

8. A composition according to claim 7, wherein the amount of component (C) is in the range from about 0.5 to about 2.5 %.
9. A composition according to claim 8, wherein component (C) is selected from alkylpolyglucoside surfactants.
- 5 10. A composition of matter from which a sanding liquid auxiliary composition according to claim 1 can be prepared by dilution with water only.
11. A process for sanding of a surface of plastic or of dried or cured paint utilizing abrasive grits and an auxiliary liquid composition that is in contact with both the surface being sanded and the abrasive grits during sanding, so as to form sanding mud on the sanded surface during sanding, wherein the improvement comprises using an auxiliary liquid composition according to claim 9.
- 10 12. A process according to claim 11, including additional steps of allowing the sanding mud produced during sanding to remain on the sanded surface for at least about 2.5 minutes after the completion of sanding, and then rinsing the sanding mud from the surface with an aqueous liquid.
- 15 13. A process according to claim 12, wherein the amount of auxiliary liquid composition is at least about 300 ml/m² of surface sanded.
14. A process for sanding of a surface of plastic or of dried or cured paint utilizing abrasive grits and an auxiliary liquid composition that is in contact with both the surface being sanded and the abrasive grits during sanding, so as to form sanding mud on the sanded surface during sanding, wherein the improvement comprises using an auxiliary liquid composition according to claim 8.
- 20 15. A process according to claim 14, including additional steps of allowing the sanding mud produced during sanding to remain on the sanded surface for at least about 2.5 minutes after the completion of sanding, and then rinsing the sanding mud from the surface with an aqueous liquid.
- 25 16. A process according to claim 15, wherein the amount of auxiliary liquid composition is at least about 300 ml/m² of surface sanded.

17. A process for sanding of a surface of plastic or of dried or cured paint utilizing abrasive grits and an auxiliary liquid composition that is in contact with both the surface being sanded and the abrasive grits during sanding, so as to form sanding mud on the sanded surface during sanding, wherein the improvement comprises using an auxiliary liquid composition according to claim 7.
18. A process according to claim 17, including additional steps of allowing the sanding mud produced during sanding to remain on the sanded surface for at least about 2.5 minutes after the completion of sanding, and then rinsing the sanding mud from the surface with an aqueous liquid.
19. A process according to claim 18, wherein the amount of auxiliary liquid composition is at least about 300 ml/m² of surface sanded.
20. A process for sanding of a surface of plastic or of dried or cured paint utilizing abrasive grits and an auxiliary liquid composition that is in contact with both the surface being sanded and the abrasive grits during sanding, so as to form sanding mud on the sanded surface during sanding, wherein the improvement comprises using an auxiliary liquid composition according to claim 7.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US94/07586

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) :C09K 3/14; B24B 1/00; B24C 1/00

US CL :51/304, 321

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 51/299,304,317,321

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	SU,A, 1,131,892 (KHARKOV POLY) 30 DECEMBER 1984 SEE ENTIRE DOCUMENT	1-20
Y	SU,A, 1,018,956 (MED TECHN DES) 23 MAY 1984 SEE ENTIRE DOCUMENT	1-20
A	SU,A, 1,362,738 (AS UKR MACROMOLECUL) 30 DECEMBER 1987, SEE ENTIRE DOCUMENT	1-20
A	SU,A, 1,234,174 (NATANSON ME) 30 MAY 1986 SEE ENTIRE DOCUMENT	1-20
A	JP,A, 56-88483 (NIPPON ZEON KK) 17 JULY 1981 SEE ENTIRE DOCUMENT	1-20
A	SUA, 929,681 (MEDICAL TECHN DES) 25 MAY 1982 SEE ENTIRE DOCUMENT	1-20

☐ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be part of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

06 SEPTEMBER 1984

Date of mailing of the international search report

SEP 19 1994

 Name and mailing address of the ISA/US
 Commissioner of Patents and Trademarks
 Box PCT
 Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

JOSEPH M. GORSKI

Telephone No. (703) 308-1805

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☒ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.